




## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

|  |  |   |   |
|--|--|---|---|
| (51) International Patent Classification <sup>5</sup> :<br>B05B 5/00, B05C 11/00, 13/00, 19/06,<br>B05D 1/02, 1/12   |  | A1  | (11) International Publication Number: WO 94/22589              |
|  |  |   | (43) International Publication Date: 13 October 1994 (13.10.94) |
| (21) International Application Number: PCT/US94/03828  |  | (81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KG, KP, KR, KZ, LK, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). |   |
| (22) International Filing Date: 7 April 1994 (07.04.94)  |  |   |   |
| (30) Priority Data:<br>5/105168 7 April 1993 (07.04.93) JP   |  |   |   |
| (71) Applicant (for all designated States except US): NORDSON CORPORATION [US/US]; 28601 Clemens Road, Westlake, OH 44145 (US).  |  | Published<br>With international search report.<br>With amended claims and statement.  |   |
| (72) Inventors; and<br>(75) Inventors/Applicants (for US only): OTANI, Tatsuo [JP/JP]; 3-11-13 Kitashinagawa, Shinagawa-ku, Tokyo (JP). TSUKAMOTO, Hidetaka [JP/JP]; 3-3-55 Minami Suita, Suita-shi, Osaka (JP). SEKIGUCHI, Makoto [JP/JP]; 31 Himewaka-cho, Myoto-ku, Nagoya-shi, Aichi-ken (JP). |  |   |   |
| (74) Agents: BURGER, Thomas, J. et al.; Wood, Herron & Evans, 2700 Carew Tower, Cincinnati, OH 45202 (US).   |  |   |   |

(54) Title: METHOD AND APPARATUS FOR COATING THREE DIMENSIONAL ARTICLES

## (57) Abstract

A method and apparatus (10) for powder coating three dimensional articles (12) carried on a conveyor (14) includes a controller (36) for controlling the rate at which coating material is discharged from a gun (16), so that the rate is proportional to the surface area of the surface portions of the article (12) as they pass the gun (16). Some surface portions topographically have a greater surface area which must be covered, while others are flat or have cut-out regions, requiring less coverage or no coverage at all. In powder coating operations, the discharge rate is controlled via automatic or programmed control of an electro-pneumatic air regulator (42) which regulates the supply of pressurized air to a powder pump (24) connected to the spray gun (16). The apparatus (10) assures uniformity in coating for a three dimensional article (12) with multiple surface portions of varying topography such as curves, angles, cut outs, etc., while minimizing the amount of wasted coating material.



**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

|    |                          |    |                                       |    |                          |
|----|--------------------------|----|---------------------------------------|----|--------------------------|
| AT | Austria                  | GB | United Kingdom                        | MR | Mauritania               |
| AU | Australia                | GE | Georgia                               | MW | Malawi                   |
| BB | Barbados                 | GN | Guinea                                | NE | Niger                    |
| BE | Belgium                  | GR | Greece                                | NL | Netherlands              |
| BF | Burkina Faso             | HU | Hungary                               | NO | Norway                   |
| BG | Bulgaria                 | IE | Ireland                               | NZ | New Zealand              |
| BJ | Benin                    | IT | Italy                                 | PL | Poland                   |
| BR | Brazil                   | JP | Japan                                 | PT | Portugal                 |
| BY | Belarus                  | KE | Kenya                                 | RO | Romania                  |
| CA | Canada                   | KG | Kyrgyzstan                            | RU | Russian Federation       |
| CF | Central African Republic | KP | Democratic People's Republic of Korea | SD | Sudan                    |
| CG | Congo                    | KR | Republic of Korea                     | SE | Sweden                   |
| CH | Switzerland              | KZ | Kazakhstan                            | SI | Slovenia                 |
| CI | Côte d'Ivoire            | LI | Liechtenstein                         | SK | Slovakia                 |
| CM | Cameroon                 | LK | Sri Lanka                             | SN | Senegal                  |
| CN | China                    | LU | Luxembourg                            | TD | Chad                     |
| CS | Czechoslovakia           | LV | Latvia                                | TG | Togo                     |
| CZ | Czech Republic           | MC | Monaco                                | TJ | Tajikistan               |
| DE | Germany                  | MD | Republic of Moldova                   | TT | Trinidad and Tobago      |
| DK | Denmark                  | MG | Madagascar                            | UA | Ukraine                  |
| ES | Spain                    | ML | Mali                                  | US | United States of America |
| FI | Finland                  | MN | Mongolia                              | UZ | Uzbekistan               |
| FR | France                   |    |                                       | VN | Viet Nam                 |
| GA | Gabon                    |    |                                       |    |                          |

## METHOD AND APPARATUS FOR COATING THREE DIMENSIONAL ARTICLES

### Field of the Invention

This invention relates to an improved method and apparatus for powder coating three dimensional articles having surface irregularities which vary in angle, curvature, and/or surface area.

5

### Background of the Invention

One common method and apparatus for coating three dimensional articles involves spray coating powder particles onto the external surface of the articles as they are conveyed by a conveyor past a spray gun. Typically, a sensor detects when an article carried by the conveyor moves into the spray pattern of the gun and signals the apparatus to spray a preset uniform quantity of powder particles to coat the article. Thus, to coat a plurality of articles, the apparatus intermittently sprays a preset, uniform quantity of coating material

10

-2-

onto each article as the articles pass the gun.

This manner of coating three dimensional articles is generally acceptable if all of the articles have a flat coating surface, or a surface which is parallel to the conveyor and perpendicular to the orientation of the gun.

However, with three dimensional articles which have surface irregularities such as cut-out regions, angled or curved surfaces, protrusions, indentations, or bent edges, etc., these surface irregularities make it difficult to uniformly coat the entire external surface of the article. One reason for this difficulty relates to the angular orientation of the surface irregularities with respect to the direction of the gun. The more the surface varies from an orientation perpendicular to the spray direction, the more difficult it becomes to adequately coat the surface. For curved or angled surfaces difficulty in coating occurs in part because an angled or curved surface has a greater density of surface area than a flat surface. This means that as the conveyor moves the three dimensional articles past the spray gun, the surface area per unit time which passes the gun is greater for angled or curved surfaces than for flat surfaces. Additionally, some surface irregularities are actually cut-out regions, which require no coating at all. Continued operation of a spray gun as a cut-out region passes by represents a waste of coating material.

-3-

Thus, as the topography of the three dimensional article varies, it becomes more difficult to uniformly coat the entire surface area, particularly for conveyors commonly used in the industry which convey such articles past the spray gun at a relatively constant speed.

One way to assure that the entire surface is coated is to operate the spray gun at a sufficiently high pressure to discharge a quantity of coating material which is greater than that which is actually necessary to coat the surface, with the pressure being determined by the portion of the surface which is most difficult to coat. This assures some coating on the most steeply angled or curved surfaces. However, a coating applied in this manner is generally not uniform due to the surface irregularities. This manner of coating also results in a tremendous amount of wasted energy and coating material.

It is an objective of this invention to improve uniformity in coating three dimensional articles with surface irregularities.

It is another objective of this invention to adequately coat the irregular surface areas of a three dimensional article while minimizing the amount of wasted coating material.

Summary of the Invention

The above-stated objectives are achieved by a method and apparatus which control the discharge rate of coating material according to the irregularity and/or area of the surface of a three dimensional article as it is conveyed past a spray gun. For powder spray coating applications, the discharge rate is controlled by regulating the air pressure input to the powder pump. This controls the volume of powder mixed into the conveying air stream moving through the pump and the rate at which the mixed powder-air stream is discharged from a spray gun toward the three dimensional article. For flat surfaces, a standard reference discharge rate is used. For steeply curved surface portions, the discharge rate increases commensurately to assure adequate coating of the increased surface density which moves past the gun per unit time. For cut-out regions, discharge of the powder is temporarily stopped to reduce waste.

Depending upon the dimensions of the articles to be coated, more than one spray gun may be necessary. Each spray gun is adapted to coat along a topographical strip, or channel, of the external surface of the article. The discharge rate for a gun dedicated to a particular channel is predetermined to correspond to the particular irregularities of the surface portions of that channel. Each gun is controlled independently, so that each channel of the

-5-

three dimensional article is coated according to a predetermined discharge sequence which corresponds uniquely to the configuration of the surface portions thereof.

By varying the discharge rate in accordance with curvature  
5 and/or surface area of the surface portions as they pass in front of a gun along a conveying path, this invention assures uniform coating of all surface portions of the article, regardless of surface irregularities. Additionally, because the discharge rate is lowered for flat surfaces, and discharge is discontinued entirely for cut-out regions, this  
10 invention reduces the amount of coating material which is wasted during the coating of three dimensional articles.

According to a preferred embodiment of the invention, a method and apparatus for coating three dimensional articles includes a conveyor, a spray gun, a powder pump, a powder hopper, a  
15 pressurized air source, a master controller, and electro-pneumatic air regulator, a position sensor for articles on the conveyor and a speed sensor for the conveyor. The conveyor carries three dimensional articles in spaced relation along the conveying path, which is oriented perpendicular to the discharge path of the spray gun. Stated another  
20 way, the discharge path of the spray gun intersects the conveying path at a 90° angle. The powder pump conveys a mixed stream of pressurized air and powder particles to the gun via a transport hose.

-6-

The powder hopper, preferably a fluidized bed, supplies powder particles to the powder pump. The pressurized air source supplies pressurized air via a supply tube to the powder pump. The electro-pneumatic air regulator is connected in the supply tube between the pressurized air source and the powder pump, and the electro-pneumatic air regulator regulates the flow rate of pressurized air supplied to the powder pump. Because the amount of powder particles drawn into the powder pump is directly proportional to the flow rate therethrough, this also controls the discharge rate from the gun.

The controller operatively connects to the electro-pneumatic air regulator and controls operation thereof according to a predetermined discharge sequence, the sequence initially determined by an operator to uniformly coat a topographical channel of the three dimensional article as the various surface portions thereof pass in front of the gun. A position sensor senses movement of an article by the conveyor into the discharge path of the gun, and thereby activates the controller to initiate the predetermined coating sequence. The conveyor speed sensor operatively connects to the controller and signals to the controller the speed of the conveyor, thereby to correlate the predetermined discharge sequence with the actual speed of the conveyor. Stated another way, the speed sensor serves



-7-

as a feedback device to the controller to assure that the predetermined coating sequence actually matches the topography of the surface portions of the channel as the article is transported in front of the gun.

5           An air pressure sensor may be located in the supply line between the electro-pneumatic air regulator and the pump, thereby to sense and provide an indication of the air pressure in the line. If desired, this air pressure can be calculated to determine, and provide a display of, the discharge rate from the gun.

10           Depending upon the transverse dimension of the articles to be coated and/or the variations in surface topography for the articles to be coated, one or more additional surface channels may be designated. This will necessitate the use of one or more additional guns, along with the corresponding additional powder supply  
15           apparatus. This additional powder supply apparatus functions in the same manner as described above, and discharge from each gun is independently controlled by the master controller. However, only a single air supply source is necessary, with a control valve located downstream thereof and operatively connected to the master  
20           controller, thereby to turn "off" or "on" all pressurized air flowing into the apparatus.

          These and other features of the invention will be more readily

understood in view of the following detailed description and the drawings.

#### Brief Description of the Drawings

5                    Fig. 1 is a schematic of a powder coating apparatus for coating three dimensional articles, in accordance with a preferred embodiment of the invention.

10                   Fig. 2 is an enlarged perspective view of a portion of the apparatus shown in Fig. 1, showing the orientation of the spray guns with respect to a three dimensional article during coating thereof.

                    Fig. 3A is a plan view of one spray coating gun during coating of a first channel of the three dimensional article shown in Fig. 2.

                    Fig. 3B is a graph which illustrates the surface area to be coated for the surface portions of the first channel shown in Fig. 3A.

15                   Fig. 3C is a graph which illustrates the quantity of coating material discharged as successive surface portions of the first channel move past the gun.

20                   Fig. 4A is a plan view of a second spray coating gun during coating of a second channel of three dimensional article shown in Fig. 2.

                    Fig. 4B is a graph which illustrates the surface area to be coated for the surface portions of the second channel shown in Fig.

4A.

Fig. 4C is a graph which illustrates the quantity of coating material discharged as successive surface portions of the second channel move past the gun.

5

Detailed Description of the Drawings

Fig. 1 schematically shows an improved spray coating apparatus 10 for powder coating a three dimensional article 12 in accordance with a preferred embodiment of the invention. While the figures show an apparatus 10 particularly suitable for powder coating, the invention is not limited thereby and is also applicable to other types of coating and coating materials. More specifically, the apparatus 10 coats a first external surface 13 of three dimensional articles 12 carried by a conveyor 14. The conveyor 14 moves the articles 12 along a conveying path and past a spray coating gun 16. The gun 16 is adapted to spray coating material along a discharge path which intersects the conveying path of the conveyor 14 at 90°. This discharge path is defined by a conical-shaped pattern 18 which is formed during operation of the gun 16 under high pressure discharge conditions.

As shown in Fig. 1, the first external surface 13 of article 12 includes first and second widths, or topographic channels 19 and 21,

-10-

respectively. As shown in Fig. 1, channel 19 is located above channel 21, though this invention is not limited to the use of a horizontal conveying path and a horizontal discharge path, and the channels may reside next to each other in the X, Y or Z planes. The number of channels depends upon the transverse dimension of the first external surface 13 with respect to the direction of the conveyor 14. As shown in Fig. 1, the conveyor 14 moves the articles 12 along a conveying path which comes out of the page, and thus the transverse dimension of external surface 13 is along the vertical, or y-axis. Another factor which plays a role in determining the number of channels, in addition to the transverse dimension, is the surface variation of the first external surface 13. For instance, channel 21 has a cut-out region while channel 19 does not..

In addition to the gun 16 for discharging coating material in a conical-shaped pattern 18 toward the first channel 19 of surface 13, Fig. 1 also shows a second gun 16a for discharging coating material in a conical-shaped pattern 18a toward the second channel 21. As described above, depending upon the number of channels and the surface configuration of first external surface 13, one or more additional guns may be added as necessary. The structural elements which supply coating material to second gun 16a are identical to the structural elements which supply first gun 16, and reference

-11-

numerals for these elements are identical, but have an "a" appended thereto. To simplify the explanation of Fig. 1, only the elements associated with first gun 16 will be described.

5 A supply hose 22 conveys a mixed stream of pressurized air and powder paint coating material to the gun 16. A powder pump 24 creates this mixture of pressurized air and coating material. The pump 24 is mounted to the top of a powder hopper 26 which maintains a fluidized bed of powder coating material. Pump 24 includes a venturi pumping chamber under negative pressure which is  
10 connected by suction tube 28 to the fluidized bed of powder in hopper 26 to draw powder into pump 24.

A pressurized air supply tube 30 defines a flow path for conveying pressurized air from a pressurized air source 32 to the pump 24. This pressurized air creates the negative pressure  
15 condition in the venturi pumping chamber of pump 24 which draws powder from hopper 26 into the pump. The supply of pressurized air from pressurized air source 32 is turned "off" and "on" via a solenoid valve 34 which is controlled by a master controller 36. The master controller 36 is preferably programmable and includes a central  
20 processing unit.

An electro-pneumatic air regulator 38 is installed in the flow path defined by supply tube 30, between the pressurized air source

-12-

32 and the pump 24. Regulator 38 is preferably a voltage to pressure regulator manufactured by Nordson Corporation of Amherst, Ohio under Part No. 113,626. An electrical signal is provided to regulator 38 via a line 40 from controller 36 indicating the air pressure to be provided at the output of regulator 38. Regulator 38 is also described in applicant's copending U.S. Application Serial Number 08/206,597, filed March 3, 1994 which is hereby incorporated by reference in its entirety. Operation of this electro-pneumatic air regulator 38 regulates the flow of pressurized air along the tube 30, which in turn regulates the amount of negative pressure in the venturi pumping chamber of pump 24 and the flow rate of the mixed powder-air stream from hopper 26 along supply tube 22, and the discharge rate of powder coating material from gun 16. Supply tube 30 also includes an air pressure sensor 42 which is operatively connected to the master controller 36, and the master controller 36 includes a display, such as an LED or LCD, for displaying the air pressure in the tube 30.

The master controller 36 also connects to position sensors 46a and 46b, which may be a light beam detector, to sense movement of the article 12 into the discharge path of the gun 16. The signal generated by the sensors 46a and 46b may then be used to actuate the master controller 36 to initiate coating.

-13-

The master controller 36 is programmed to control the operation of the regulator 38 (and regulator 38a) according to a predetermined coating sequence. This coating sequence may involve increasing or decreasing the supply of pressurized air to the pump 24 from regulator 38, thereby to increase or decrease the discharge rate of coating material from the gun 16 in accordance with the particular surface configuration or topography of the channel 19 (and channel 21). For instance, if the surface channel 19 includes flat portions and angled portions or curved portions, i.e. portions not parallel to the conveying path, the surface area of the non-parallel portions which pass by the gun 16 per unit time will be greater than the surface area of the flat portions which pass by the gun 16 per unit time, assuming the conveyor 14 moves at a constant speed. As described in more detail below with respect to Fig. 2, these uneven or non-parallel portions therefore require a higher discharge rate, with the discharge rate being commensurate with the slope of a tangent line to the surface.

If desired, the speed of the conveyor 14 may be fed back to the master controller 36. This may be done by fixing a rotatable spool 48 in contact with the conveyor 14 so that the spool 48 rotates upon movement of the conveyor 14. An axle 50 connects to the spool 48 and supports a disc 52 which rotates therewith. The

-14-

disc 52 is coded via punched out regions at a diameter which corresponds to a location of light beam sensors 54a and 54b. As the disc 52 rotates, the passage or obstruction of the light beam between sensors 54a and 54b indicates to the master controller 36 the speed of the conveyor 14. In its simplest form, with uniformly spaced punch-out regions in the disc 52, this structure may be used simply to indicate to the master controller 36 the speed of the conveyor 14 and whether the conveyor 14 has stopped or started, via sensing at the controller 36 the rate of receipt of the "obstructed" and "unobstructed" signals. If the conveyor 14 always runs at the same speed to coat the same articles 12, this speed sensing structure may not be necessary, because the predetermined coating sequences can be correlated to the channel or channels of the article 12 in relation to that constant speed. However, this added degree of control is preferable because of possible fluctuations in the speed of the conveyor 14 and/or the desire to operate the conveyor 14 at different speeds for coating different articles 12.

If desired, the coding on the disc 52 may be specific to a particular article 12, and arranged such that one complete rotation of disc 52 corresponds to movement of the conveyor 14 from the leading edge of one article 12 to the leading edge of the next succeeding article 12. Each surface portion to be coated can then be



-15-

correlated to an arcuate section of the disc 52. The spacing of the cut out regions could then dictate the discharge rate. Thus, the invention contemplates added levels of feedback control, if desired.

Fig. 2 shows the first external surface 13 of article 12 in greater detail. More particularly, Fig. 2 shows the topographic surface details of first upper channel 19 and second lower channel 21. The surfaces of channels 19 and 21 are coated by material discharged from gun 16 and 16a, respectively, as the article 12 moves along the conveying path in a direction designated by reference numeral 56. Channel 19 includes multiple surface portions, designated 19a, 19b, 19c, 19d and 19e. Surface portion 19a is oriented parallel to the discharge path of the gun 16 and perpendicular to the conveying path of the conveyor 14. Surface portion 19b is parallel to the conveying path and perpendicular to the discharge path. Surface portion 19c is curved, and a tangent line to this curve is almost parallel with the discharge path adjacent portion 19b, but becomes almost perpendicular to the discharge path as the surface portion 19c flattens, adjacent the flat or parallel surface portion 19d. Surface portion 19e is oriented parallel with the discharge path and perpendicular to the conveying path. Surface portions 21a, 21b, 21c and 21d are similar to surface portions 19a, 19b, 19c and 19d, respectively. However, channel 21 also includes

-16-

a cut-out region 21e which does not require discharge of any coating material, followed by a flat surface portion 21f and a perpendicular surface portion 21g.

As shown in Fig. 2, if article 12 is moved past guns 16 and 16a at a constant rate of speed, a greater surface area of the article 12 passes the guns 16 and 16a per unit time during passage of those portions which are non-parallel to the conveying path i.e. such as portions 19c and 21c. Also, the greater the curvature, or angle of the surface portions with respect to the conveying path, the greater the amount of surface area which passes the guns 16 and 16a per unit time. Thus, to uniformly coat surface portions 19b and 19c with a layer of coating material of uniform thickness, and to minimize waste of coating material, more coating material must be discharged as portion 19c passes gun 16 than when portion 19b passes gun 16, assuming the conveyor 14 operates at constant speed.

Subsequently, as surface portion 19c levels off toward surface portion 19d, the needed volume of coating material decreases. The effect is similar for channel 21, but channel 21 also includes cut-out 21e, which requires no coating material to be discharged.

To accomplish the desired increases and decreases in quantity of coating material discharged, as dictated by the surface configuration of the channels 19 and 21, the master controller 36

-17-

controls the flow rate of pressurized air along tube 30 by means of regulator 38. For a portion which is flat, such as 19b and 21b, the standard reference for surface area passing gun 16 per unit time is 1.0 and the standard reference for quantity discharged is also 1.0.

5 When a curved portion such as 19c moves in front of the gun 16, (adjacent portion 19b) the initial surface area which passes gun 16 per unit time is about 4.4 times the reference value region. As the angle of surface portion 19c decreases to about 30°, (adjacent portion 19d) the region which passes gun 16 per unit time is about 1.15 times the standard reference value.

10 Thus, the apparatus 10 opens up or closes down the flow passage in regulator 38, under the control of controller 36, to increase or decrease, respectively, the discharge rate from guns 16 and 16a relative to the surface area of the respective channel 19 or 21. Thus, for example, the flow passage through regulator 38 15 would be opened wider during the coating of portion 19c, than during the coating of portion 19b. This results in the most efficient use of the coating material, since excess coating material is not discharged onto flat portions, and additional material is discharged on curved portions to accomodate the additional surface area defined by the 20 surface topography. Additionally, coating material is saved because the apparatus 10 does not discharge coating material toward cut-out

-18-

regions, such as portion 21e.

For portions which are substantially parallel to the discharge path, such as portions 19a, 21a, 19e, and 21g, it is extremely difficult to uniformly coat the exposed surface area, due to the angular orientation of the surface with respect to the guns 16 and 16a. Therefore, it is desirable to electrostatically charge the powder particles to promote attraction toward these surfaces and uniform coverage thereof. Electrostatic charging of the powder particles may occur via use of a corona charging electrode external to the guns 16 and 16a, though it is preferable to electrostatically charge the powder particles while in the apparatus 10, either via an internal corona electrode or an internal charging system such as a triboelectric friction charging system. Moreover, this type of electrostatic powder coating gun is preferably also used for coating the other portions of the article 12 as well.

Fig. 3A shows topographic channel 19 in plan view, and particularly surface portions 19a, 19b, 19c, 19d and 19e. Fig. 3B includes a curve 58 which graphically illustrates the surface area of channel 19 which passes in front of gun 16 during movement of the conveyor 14. For instance, the surface area represented for portions 19a and 19d are equal to the standard reference value 1.0. The surface area represented for the slightly inclined region of portion 19c

-19-

is 1.15 times the reference value, while the surface area for the steeper region of portion 19c increases from 1.15 to 4.4 of the reference value. For curved portions such as 19c, Fig. 3B also reflects the slope of a tangent line to the surface.

5                    Fig. 3C graphically illustrates the quantity of coating material which should be discharged according to the invention as surface portions 19a, 19b, 19c, 19d and 19e pass in front of gun 16. This quantity is represented by curve 60. The shaded region located above curve 60, and designated by reference numeral 62, represents  
10                    the amount of coating material that is saved by using this invention, since without this invention it would otherwise be necessary to discharge at a rate sufficient to cover the steepest region of surface portion 19c. The other option of course, though equally undesirable, would be to discharge at a rate insufficient to adequately coat the  
15                    steepest region of surface portion 19c.

                    Figs. 4A, 4B and 4C correspond to Figs. 3A, 3B and 3C, respectively, but relate to coverage of second topographic channel 21. Curve 64 in Fig. 4B shows the surface area for portions 21a, 21b, 21c, 21d, 21e, 21f and 21g of channel 21, and curve 66 in Fig.  
20                    4C graphically shows the quantity of coating material discharged as these surface portions pass the gun 16a. Also, the reference numeral 68 designates the amount of coating material saved with

-20-

this invention by varying the discharge rate.

Compared to Figs. 3A, 3B and 3C, Figs. 4A, 4B and 4C differ only in respect to the cut-out portion 21e, which does not require any coating material. The second discharge path 18a and the second gun 16a are necessary for coating article 12 because of the different surface configurations, or surface topography, represented by the cut-out region 21e. In some cases, as explained previously, additional or fewer guns may be needed, but the number of guns necessary will be determined by the transverse dimension of the article 12 and the number of topographic variations in the surface orientation of the article 12. The invention requires one gun, and therefore one topographic channel, for each variation and surface orientation across the transverse dimension of the article 12.

While the preferred embodiment of the invention has been described, it is to be understood that modifications may be made to the preferred embodiment without departing from the scope of the invention. Accordingly, applicant wishes to be bound only by the claims appended hereto.

We Claim:

-21-

1. An apparatus for powder coating a three dimensional article having an external surface of at least two varying topographical surface portions, comprising:

a gun aimed in a discharge direction;

5 means for conveying, relative to the gun, the article along a conveying path to successively convey the surface portions past the gun;

a powder pump operatively connected to the gun;

means for supplying fluidized powder particles to the pump;

10 means for supplying pressurized air to the pump via a flow path, the pump adapted to combine the pressurized air and powder particles in a mixed stream and to convey the powder-air stream along a transport path to the gun for discharge therefrom toward the surface;

15 flow control means located in the flow path and adapted to regulate the flow of pressurized air therethrough, thereby to regulate the flow rate of the mixed powder-air stream conveyed to the gun and discharged therefrom; and

20 a controller operatively connected to the flow control means, the controller adapted to control the flow control means to control the discharge rate of the stream from the gun according to a predetermined discharge sequence which corresponds to the

-22-

topography of the surface portions as the portions pass in front of the gun, thereby to promote uniform coating of the surface portions and reduced waste of powder particles during coating of the article.

5

2. The apparatus of claim 1 and further comprising:

a sensor operatively connected to the controller and adapted to sense the article as it moves in front of the gun and to signal the controller to initiate the predetermined discharge sequence.

10

3. The apparatus of claim 1 and further comprising:

speed sensing means operatively connected to the controller and adapted to determine the rate of speed of the conveying means, thereby to correlate the predetermined discharge sequence with the rate at which the surface portions pass in front of the gun.

15

4. The apparatus of claim 1 and further comprising:

an air pressure sensor located in the flow path between the flow control means and the pump; and

display means operatively connected to the air pressure sensor for indicating the air pressure in the flow path.

20



-23-

5. The apparatus of claim 1 and further comprising:  
means for electrostatically charging the particles in the stream.

5

6. The apparatus of claim 5 wherein the electrostatic charging  
means is located in the transport path.

10

7. The apparatus of claim 1 wherein the flow control means  
comprises an electro-pneumatic regulator which receives an electrical  
signal from the controller and in response varies the output pressure  
of air supplied from the regulator.

15

8. The apparatus of claim 1 wherein the gun remains in a fixed  
position and the conveying means comprises a conveyor which  
carries the article past the gun.

20

9. The apparatus of claim 1 and further comprising:  
a second gun adapted to discharge pressurized air and powder  
particles in a second stream toward successively conveyed surface  
portions of the article, the second gun and the first gun arranged  
along a line perpendicular to the conveying path and the discharge  
direction.

-24-

10. A coating apparatus comprising:

a conveyor for conveying a three dimensional article along a conveying path, the article having an external surface with a plurality of surface portions of varying topography at least one of which portions is not parallel to the conveying path;

a gun aimed along a discharge path which intersects the conveying path;

means for supplying a coating material to the gun in a pressurized condition for discharge therefrom to coat the surface portions as the article is moved through the discharge path via the conveyor; and

a controller operatively connected to the supplying means and adapted to variably control the discharge rate of the coating material according to a predetermined discharge sequence so that the discharge rate for each surface portion is commensurate with the surface area thereof, thereby to uniformly coat the surface portions and minimize waste of coating material.

11. The apparatus of claim 10 and further comprising:

a sensor operatively connected to the controller and adapted to sense the article as it moves in front of the gun and to signal the controller to initiate the predetermined discharge sequence.

-25-

12. The apparatus of claim 10 and further comprising:

speed sensing means connected to the controller and adapted to determine the rate of speed of the conveying means, thereby to correlate the predetermined discharge sequence with the rate at which the surface portions pass in front of the gun.

5

13. The apparatus of claim 10 and further comprising:

air pressure sensing means operatively connected to the supplying means and adapted to sense and display a parameter proportional to the discharge rate.

10

14. The apparatus of claim 10 and further comprising:

means for electrostatically charging the particles in the stream.

15

15. The apparatus of claim 10 wherein the gun remains in a fixed position and the conveying means comprises a conveyor which carries the article past the gun.

-26-

16. The apparatus of claim 10 and further comprising:

a second gun adapted to discharge coating material along a second discharge path which also intersects the conveying path as the article moves along the conveying path, the second gun and the first gun arranged along a line perpendicular to the conveying path and the discharge paths.

5

-27-

17. A method of coating comprising the steps of:

moving a three dimensional article to be coated along a conveying path relative to a spray gun, the gun aimed along a discharge path generally perpendicular to and intersecting the conveying path, the article having an external surface to be coated with a plurality of surface portions having varying surface topography and surface area;

discharging a coating material from the gun along the discharge path to successively coat the surface portions as the article moves along the discharge path; and

controlling the discharge rate of the coating material according to a predetermined coating sequence, the rate being dependent upon the surface topography and the surface area of the portion located in the discharge path, thereby to uniformly coat the surface portions while minimizing the amount of wasted coating material.

18. The method of claim 17 wherein the coating material is powder and further comprising the step of:

electrostatically charging the discharged particles.

19. The method of claim 18 wherein the charging occurs inside the gun.

-28-

20. The method of claim 17 and further comprising the step of:  
sensing the article as it moves into the discharge path, thereby  
to actuate the controller to initiate the predetermined coating  
sequence.

5

21. The method of claim 17 and further comprising the step of:  
measuring the speed at which the article is moved through the  
discharge path and along the conveying path; and  
inputting the measured rate to the controller to control the  
predetermined coating sequence.

10

**AMENDED CLAIMS**

[received by the International Bureau on 13 September 1994 (13.09.94);  
original claims 10,13,17 and 18  
amended remaining claims unchanged (5 pages)]

10. A powder coating apparatus comprising:
- a conveyor for conveying a three dimensional article along a conveying path, the article having an external surface with a plurality of surface portions of varying topography, at least one of which portions is not parallel to the conveying path;
- a gun aimed in a discharge direction;
- means for flowing powder particles to the gun in a pressurized condition and for discharging the particles therefrom to powder coat the surface portions as the article is moved through the discharge path via the conveyor, the means for flowing including means for supplying pressurized air to the gun, thereby to combine the pressurized air and the powder particles in a mixed stream for subsequent discharge from the gun and toward the surface portions; and
- a controller operatively connected to the means for flowing and the means for supplying pressurized air, the controller adapted to vary the flow of the pressurized air from the means for supplying pressurized air, thereby to variably control the discharge rate of the powder particles in the mixed stream according to a predetermined discharge sequence so that the discharge rate for each surface portion is commensurate with the surface area thereof, thereby to uniformly powder coat the surface portions and to minimize waste of the powder particles.

11. The apparatus of claim 10 and further comprising:  
a sensor operatively connected to the controller and adapted to sense the article as it moves in front of the gun and to signal the controller to initiate the predetermined discharge sequence.

12. The apparatus of claim 10 and further comprising:  
speed sensing means connected to the controller and adapted to determine the rate of speed of the conveying means, thereby to correlate the predetermined discharge sequence with the rate at which the surface portions pass in front of the gun.

13. The apparatus of claim 10 and further comprising:  
air pressure sensing means operatively connected to the flowing means and adapted to sense and display a parameter proportional to the discharge rate.

14. The apparatus of claim 10 and further comprising:  
means for electrostatically charging the particles in the stream.



15. The apparatus of claim 10 wherein the gun remains in a fixed position and the conveying means comprises a conveyor which carries the article past the gun.

16. The apparatus of claim 10 and further comprising:  
a second gun adapted to discharge coating material along a second discharge path which also intersects the conveying path as the article moves along the conveying path, the second gun and the first gun arranged along a line perpendicular to the conveying path and the discharge paths.

17. A method of powder coating comprising the steps of:
- moving a three dimensional article to be powder coated along a conveying path relative to a spray gun, the gun aimed along a discharge path generally perpendicular to and intersecting the conveying path, the article having an external surface to be powder coated, the external surface having a plurality of surface portions with varying surface topography and surface area;
  - mixing powder particles and pressurized air in the gun to form a mixed stream, the powder particles supplied by a powder source and the pressurized air supplied by a pressurized air source;
  - discharging the mixed stream from the gun toward the discharge path to successively powder coat the surface portions as the article moves into the discharge path; and
  - controlling the discharge rate of the mixed stream according to a predetermined coating sequence by varying the flow of pressurized air from the pressurized air source, the discharge rate being dependent upon the surface topography and the surface area of the portion located in the discharge path, thereby to uniformly powder coat the surface portions while minimizing the amount of wasted powder.

18. The method of claim 17 and further comprising the step of:  
electrostatically charging the discharged particles.
19. The method of claim 18 wherein the charging occurs inside  
the gun.
20. The method of claim 17 and further comprising the step of:  
sensing the article as it moves into the discharge path,  
thereby to actuate the controller to initiate the predetermined coating  
sequence.
21. The method of claim 17 and further comprising the step of:  
measuring the speed at which the article is moved through  
the discharge path and along the conveying path; and  
inputting the measured rate to the controller to control the  
predetermined coating sequence.

**STATEMENT UNDER ARTICLE 19**

The search report for applicant's above-identified PCT application identified eighteen documents considered to be relevant. Five were designated "X" or "Y", and the other thirteen were designated "Y", with respect to one or more of the claims.

Applicant submits herewith substitute pages 24 and 27 which include amended claims 10 and 17, respectively. Substitute pages 25, 26 and 28 have also been submitted to now include claims 11-14, 15-16 and 18-21, respectively, to accommodate the increased lengths of amended claims 10 and 17. Also, claims 13 and 18 have been amended for consistency.

With this amendment to claims 10 and 17, each of the independent claims of this application, i.e. claims 1, 10 and 17, now includes specific reference to powder coating, along with the feature of

varying the flow of the pressurized air which controls discharge of the particles, in response to the topography of the article being coated. This results in uniform coating of the article and minimum powder waste.

For instance, claim 1 includes a powder pump, means for supplying fluidized powder particles to the pump and means for supplying pressurized air to the pump. Additionally, a flow control means regulates the flow of pressurized air, thereby to regulate the flow rate of the mixed stream conveyed to and discharged therefrom.


Similarly, claim 10 includes a means for flowing powder particles to a gun in a pressurized condition and for discharging the particles therefrom, thereby to powder coat surface portions of an article as the article is moved through a discharge path by a conveyor. The means for flowing includes means for supplying pressurized air to the gun, thereby to combine the pressurized air and the powder particles in a mixed stream for subsequent discharge from the gun and toward the surface portions. A controller varies the flow of the pressurized air, thereby to variably control the discharge rate according to a predetermined discharge sequence so that the discharge rate for each surface portion is commensurate with the surface area thereof.




Claim 17 recites a method of powder coating an article which includes mixing powder particles and pressurized air to form a mixed stream, wherein the powder particles are supplied by a powder

source and the pressurized air is supplied by a pressurized air source.




Claim 17 further includes discharging this mixed stream toward a discharge path to successively powder coat surface portions of the article as the article moves along the discharge path. Claim 17 also includes controlling the discharge rate of the mixed stream according to a predetermined coating sequence, by varying the flow of pressurized air from the pressurized air source. The discharge rate is thus dependent on the surface topography of the portion located in the discharge path.

As amended, applicant respectfully maintains that each of independent claims 1, 10 and 17, and also the dependent claims, now recites a combination of elements or steps which is novel, involves an inventive step and has industrial applicability.









## INTERNATIONAL SEARCH REPORT

International application No.

PCT/US94/03828

**A. CLASSIFICATION OF SUBJECT MATTER**

IPC(5) :B05B 5/00; B05C 11/00, 13/00, 19/06; B05D 1/02, 1/12

US CL :Please See Extra Sheet.

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 118/308, 310, 313, 315, 324, 668, 669, 676, 677, 679, 683, 684, 696, 697, 621, 622, 627; 427/180, 189, 475, 483, 424

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

| Category*      | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No.               |
|----------------|--|-------------------------------------|
| X<br>----<br>Y | US, A, 3,593,308 (FAGAN) 13 July 1971, see entire document.                        | 17<br>----<br>1-16, 18-21           |
| X<br>----<br>Y | US, A, 3,594,211 (DRUM) 20 July 1971, see entire document.                         | 17, 18, 20<br>-----<br>1-16, 19, 21 |
| Y              | US, A, 3,054,697 (IRLAND ET AL) 18 September 1962, see entire document.            | 5, 6, 14, 18                        |
| Y              | US, A, 3,691,991 (LUDERER ET AL) 19 September 1972, see entire document.           | 1, 5, 6                             |
| Y              | US, A, 3,245,376 (ROMSTADT) 12 April 1966, see entire document.                    | 1-21                                |

☒ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

|   |     |  |
|---|-----|--|
| * Special categories of cited documents:  | *T  | later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention  |
| *A* document defining the general state of the art which is not considered to be part of particular relevance   | *X* | document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone   |
| *E* earlier document published on or after the international filing date  | *Y* | document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art |
| *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) | *Z* | document member of the same patent family  |
| *O* document referring to an oral disclosure, use, exhibition or other means  |     |  |
| *P* document published prior to the international filing date but later than the priority date claimed  |     |  |

Date of the actual completion of the international search

23 JUNE 1994

Date of mailing of the international search report

20 JUL 1994

 Name and mailing address of the ISA/US  
 Commissioner of Patents and Trademarks  
 Box PCT  
 Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

STEVEN P. GRIFFIN

Telephone No. (703) 308-0651

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/US94/03828

## C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

| Category* | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claims No.    |
|-----------|--|---------------------------|
| Y         | US, A, 5,056,462 (PERKINS ET AL) 15 October 1991, see entire document.             | 1-21                      |
| Y         | US, A, 3,777,702 (FITZGERALD) 11 December 1973, see entire document.               | 1-21                      |
| Y,P       | US, A, 5,202,214 (KAWAMORITA ET AL) 13 April 1993, see entire document.            | 5, 9, 14, 16, 18          |
| Y         | US, A, 4,448,819 (BUSCHOR) 15 May 1984, see entire document.                       | 1-21                      |
| X         | GB, A, 2,169,724 (GIBSON) 16 July 1986, entire document.                           | 17, 20, 21                |
| ---       |  | -----                     |
| Y         |  | 1-16, 18, 19              |
| Y,P       | US, A, 5,217,745 (PATEL) 08 June 1993, see entire document.                        | 3, 21                     |
| Y         | US, A, 5,131,350 (BUSCHOR) 21 July 1992, see entire document.                      | 4, 13                     |
| Y         | US, S, 3,556,255 (LOMAX, JR.) 19 January 1971, see entire document.                | 19                        |
| Y         | US, A, 3,263,127 (POINT ET AL) 26 July 1996, see entire document.                  | 19                        |
| Y         | US, A, 4,572,103 (ENGEL) 25 February 1986, see column 3, lines 29-37.              | 7                         |
| Y         | SU, A, 1,087,191 (LAKOKRASPOKRYTIE) 23 April 1984, see English abstract.           | 1, 4, 7, 13               |
| X         | SU, A, 1,323,138 (MOLCHKOV) 15 July 1987, see English abstract.                    | 10, 11, 15, 17, 20        |
| ---       |  | -----                     |
| Y         |  | 1-9, 12-14, 16, 18-19, 21 |
| X         | SU, A, 1,358,998 (LAKOKRASPOKRYTE) 15 December 1987, see English abstract.         | 17, 20                    |
| ---       |  | -----                     |
| Y         |  | 1-16, 18, 19, 21          |

# INTERNATIONAL SEARCH REPORT

International application No.

PCT/US94/03828

## A. CLASSIFICATION OF SUBJECT MATTER:

US CL :

118/308, 310, 313, 315, 324, 668, 669, 679, 683, 696, 621; 427/180, 475, 483, 424